

Performance

A specially formulated HDPE ideal designed to exhibit low gel levels with good dimensional stability and stiffness. A superior product that offers excellent cold temperature durability and outdoors. Treated two sides for excellent printability by flexo, and thermal transfer.

Gauge:	7.5 mil	-
Yeild @ 1mil:	27,585 in ² /lb	-
Gloss (45°):	8%	D-2457
Tensile - lbs/in (MD/TD):	4,550 / 4,250	D-882
Elongation (MD/TD):	1,200% / 1,200%	D-882
Secany Modulus - lbs/in (MD/TD):	98,000 / 125,000	D-882
Elmendorf Tear - lbs (MD/TD):	0.44 / 2.2	D-1922
Dart Impact - lbs:	0.88	D-1709

Storage Conditions

Unless otherwise specified in this document, ideally store at 72F and 50% RH.

End Uses

Lumber tags, horticultural tags, temporary ID & membership cards, shelf talkers, and freezer case dividers.

Disclaimer: The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All of our products are sold subject to Trebnick System's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.