


# TT492



## Labels for Life.



**Face Stock:** 1.6 mil topcoated gloss white polyimide film offering excellent chemical resistance combined with superior high heat resistance. The material will not curl and is designed to survive high temperatures of lead-free solder processes.

**Adhesive:** 1.1 mil high performance permanent acrylic pressure sensitive adhesive offering exceptional resistance to harsh PCB cleaning solvents and high heat.

**Release Liner:** 2.7 mil glassine liner designed to offer excellent performance.

## Thermal Transfer Gloss White Polyimide Film

TT492 is designed for thermal transfer printing of variable information for circuit board labeling. This LOW PROFILE high performance label withstands multiple passes through inline and batch cleaning processes; as well as very good resistance to most fluxes. TT492 performs well through most lead and lead-free reflow processes.

## Typical Industry Sectors

Electronics

Medical

Industrial

# TT492

Thermal Transfer Gloss White Polyimide Film



Labels for Life.



## Agency Recognitions



### Adhesion

Stainless Steel	20 minute dwell	22 oz/in (24 N/100mm)
	24 hours dwell"	29 oz/in (32 N/100mm)



### Material Caliper

See following charts for specific details.



### Exterior Durability

Recommended for indoor use only.



### Temperature Range

See following charts for specific Temperature Ranges.



### Shelf Life

Recommended Storage conditions : 40°F (5°C) - 80°F (26°C) and 40-70% RH.  
Shelf Life: 2 years @ recommended storage



### Recommended Ribbons

#### Thermal Transfer Printing

TTRR-B Resin Ribbon	TTRR-CR Resin Ribbon
TTRR-D Resin Ribbon	

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 10/5/23

#### UNITED STATES HEADQUARTERS

28164 W. Concrete Drive,  
Ingleside, IL 60041 USA  
Phone: +1 (815) 385 - 0011  
Fax + (815) 385 - 0359

#### MEXICO MONTERREY

Carretera a Laredo KM 16.5  
Bodega 14B Colonia Moisés Sáenz  
Apodaca, Nuevo León CP 66613  
Phone: +52 (81) 8008 - 0438

#### EUROPE GERMANY

Güterbahnhofstraße 3-7  
63450 Hanau  
Phone: +49 (6181) 440 830 - 0  
Fax: +49 (6181) 440 830 - 99

# TT492

Thermal Transfer Gloss White Polyimide Film



Labels for Life.

## Product Details

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 Substrate (Topcoat & Film) Adhesive Liner (Glassine) Total	0.0016 inch (0.0406 mm) 0.0011 inch (0.027 mm) 0.0027 inch (0.070 mm) 0.0054 (0.137 mm)
Adhesion to: Stainless Steel	ASTM D 1000 20 minute dwell 24 hours dwell	22 oz/in (24 N/100mm) 29 oz/in (32 N/100mm)
Dielectric Strength	ASTM D1000	10,000 volts

## Performance Properties

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Short Term High Service Temperature	80 seconds at 572F (300C)	No visible effect
	5 minutes at 500F (260C)	No visible effect
	2 hours at 338F (170C)	No visible effect
Long Term High Service Temperature	1000 hours at 212F (100C)	No visible effect
Low Service Temperature	1000 hours at -94F (-70C)	No visible effect
Humidity Resistance	1000 hours at 98F (37C), 95% R.H.	No visible effect
UV Light Resistance	30 days in UV Sunlighter 100	Topcoat turns yellow, label remains functional
Weatherability	1000 hours in Xenon Arc Weatherometer	Slight discoloration
Salt Fog Resistance	ASTM B 117 30 days in 5% salt fog solution chamber	No visible effect
Abrasion Resistance	Taber Abraser, CS-10 grinding wheels, 500 g/arm (Fed. Std. 191A, Method 5306)	Print legible after 100 cycles
Chemical Vapor Phase Resistance	Labels adhered to epoxy PC board and exposed to the vapor of the boiling chemical for 10 minutes and then rubbed with a cotton swab saturated with the chemical for 10 rubs.  Testing samples were baked 4 minutes at 160C prior to testing  Ionox 3955 Micronox MX2501	Severe print removal Complete print removal

Performance properties tested on TT492 printed with IDENTCO Series TTRR-D thermal transfer ribbon. Printed samples of TT492 were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environmental conditions. \* TT492 is not recommended for outdoor use.

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 10/5/23

### UNITED STATES HEADQUARTERS

28164 W. Concrete Drive,  
Ingleside, IL 60041 USA  
Phone: +1 (815) 385 - 0011  
Fax + (815) 385 - 0359

### MEXICO MONTERREY

Carretera a Laredo KM 16.5  
Bodega 14B Colonia Moisés Sáenz  
Apodaca, Nuevo León CP 66613  
Phone: +52 (81) 8008 - 0438

### EUROPE GERMANY

Güterbahnhofstraße 3-7  
63450 Hanau  
Phone: +49 (6181) 440 830 - 0  
Fax: +49 (6181) 440 830 - 99

# TT492

Thermal Transfer Gloss White Polyimide Film



Labels for Life.

## Performance Properties

PERFORMANCE PROPERTIES		CHEMICAL RESISTANCE			
CHEMICAL REAGENT	EFFECT TO LABEL	SUBJECTIVE OBSERVATION OF VISIBLE CHANGE			
		RIBBON PERFORMANCE: TTRR-B, TTRR-CR, TTRR-D			
		WITHOUT RUB		WITH RUB	
			TTRR-B	TTRR-CR	TTRR-D
Kyzen Corp. 15% Aquanox® A4625 at 140F (60C)	No visible effect	1	2	1	2
Kyzen Corp. 17% Aquanox® A4520 at 140F (60C)	No visible effect	1	1	1	1
Kyzen Corp. 10% Aquanox® A4638 at 150F (65C)	No visible effect	1	1	1	1
Kyzen Corp. 20% Aquanox® A4703 at 145F (63C)	No visible effect	1	3	1	1
Zestron, 15% Atron® AC205 at 150F (65)	No visible effect	1	3	1	1
Zestron, 15% Atron® AC207 at 150F (65)	No visible effect	1	3	2	3
Zestron, 15% Vigon® A201 at 150F (65)	No visible effect	1	3	2	1
Zestron, 15% Vigon® N600 at 150F (65)	No visible effect	1	3	1	1
Isopropyl Alcohol 99% at 180F (82C)	No visible effect	1	1	1	1
Deionized Water AT 212F (100C)	No visible effect	1	1	1	1

Samples printed with TTRR-B, TTRR-CR, & TTRR-D thermal transfer ribbons. Samples laminated to epoxy PC board. Test samples exposed to indicated environments. Test samples baked 4 minutes at 160°C before testing. All test samples were immersed in the test fluids for 10 minutes. Samples were rubbed 10 times with cotton swab saturated with the test fluid.

Rating Scale: 1=no visible effect. 2=slight smear or print removal, detectable but minimal smear. 3=moderate smear or print removal (print still legible). 4=severe smear or print removal (print illegible or just barely legible). 5=complete print removal

PERFORMANCE PROPERTIES		CHEMICAL RESISTANCE
Solvent Resistance TEST FLUID		MIL-STD202G, Method 215K RESULTS TTRR-D
Solvent A	part IPA, 3 parts mineral spirits	Meets Requirement
Solvent B	Terpene Defluce	Meets Requirement
Solvent C	Saponifier @ 70	Meets Requirement

Test samples were printed with TTRR-D thermal transfer ribbon. Labels were printed with alphanumerics and barcodes. Test samples were subjected to 3 cycles of 3 minute immersions immediately followed by a toothbrush rub after each immersion.

Product testing, customer feedback and history of similar products support a customer performance expectation of at least two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment between 45-90°F (7-32°C) and 20-75% RH. We are confident that our product will perform well beyond this time frame however it remains the responsibility of the user to assess the risk of using such product. We encourage customers to develop functional testing protocols that will qualify a product's fitness for use in their actual applications.

Trademarks: ANSI: American National Standards Institute (U.S.A.) • ASTM: American Society for Testing and Materials (U.S.A.) • All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units • Aquanox® is a registered trademark of the Kyzen Corporation • Atron® is a registered trademark of Zestron Corporation • Ionox® is a registered trademark of the Kyzen Corporation • Micronox® is a registered trademark of the Kyzen Corporation • Polyken™ is a trademark of Testing Machines Inc. • PSTC: Pressure Sensitive Tape Council (U.S.A.) • UL: Underwriters Laboratories Inc. (U.S.A.) • Vigon® is a registered trademark of Zestron Corporation • Weather-Ometer® is a registered trademark of Atlas material Testing Technology LLC

Material may not be reproduced or distributed in any form with written permission.

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 10/5/23

### UNITED STATES HEADQUARTERS

28164 W. Concrete Drive,  
Ingleside, IL 60041 USA  
Phone: +1 (815) 385 - 0011  
Fax + (815) 385 - 0359

### MEXICO MONTERREY

Carretera a Laredo KM 16.5  
Bodega 14B Colonia Moisés Sáenz  
Apodaca, Nuevo León CP 66613  
Phone: +52 (81) 8008 - 0438

### EUROPE GERMANY

Güterbahnhofstraße 3-7  
63450 Hanau  
Phone: +49 (6181) 440 830 - 0  
Fax: +49 (6181) 440 830 - 99